



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLÓN

C.I.F.: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLÓN
TEL: 964 208 583 - FAX: 964 723 141
www.laboratoriocarpi.com

TEST REPORT

PETITIONER: MOSAVIT ALCALATEN, S.L.
ADDRESS: Carretera Alcora-Lucena Km 11,5
CITY: LUCENA DEL CID (Castellón)
TEST REPORT Nº: 51.906
PAGE Nº: 1 / 5
DATE OF TEST REPORT: 12/09/2012
DATE OF RECEIPT OF THE SAMPLE: 03/09/2012
DATE OF TESTS PERFORMANCE: 03 - 10/09/2012
NUMBER OF TILES SUPPLIED: 10 sheet of 11 x 31 cm

DESCRIPTION OF THE SAMPLE:

Glass mosaic, 25 x 25 mm. Ref.:

-- **MOSAICO VITREO 25 x 25 mm** --

Code lab.: 299-12

TEST PERFORMED:

- UNE-EN-ISO 10545-3 : DETERMINATION OF WATER ABSORPTION.
- UNE-EN-ISO 10545-9 : DETERMINATION OF RESISTANCE TO THERMAL SHOCK.
- UNE-EN-ISO 10545-13 : DETERMINATION OF CHEMICAL RESISTANCE.
- UNE-EN-ISO 10545-14 : DETERMINATION OF RESISTANCE TO STAINS.



José A. Estibález Catalán
MANAGER

The samples and his description have been chosen by the petitioner.

The reported results relate only to the samples tested.

This report must not be reproduced in part without the written permission of Laboratory.

The uncertainties have been evaluated according to recommendations of the document ISO/TAG5/WGE : June 95.



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLÓN

C.I.F.: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLÓN
TEL: 964 208 583 - FAX: 964 723 141
www.laboratoriocarpi.com

Test report nº: 51.906

Page nº : 2 / 5

Petitioner: MOSAVIT

Date: 12/09/2012

DETERMINATION OF WATER ABSORPTION

DESCRIPTION OF THE SAMPLE.-

Glass mosaic, 25 x 25 mm. Ref.:

-- **MOSAICO VITREO 25 x 25 mm** --

Code lab.: 299-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 3:1997**)

* Water absorption for each tile (**Boiling method "E_b"**):

<u>Tile</u>	<u>Water absorption (E_b)</u> (%)
1	0.1
2	0.1
3	0.0
4	0.1
5	0.1

* Average water absorption of the sample: **0.1 %**

* Measurement uncertainty: **U = ± 0.1 % (k=2)**

* Average value uncertainty: **U = ± 0.1 % (k=2)**



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL INGENIEROS INDUSTRIALES
CASTELLÓN



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLÓN

C.I.F.: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLÓN
TEL: 964 208 583 - FAX: 964 723 141
www.laboratoriocarpi.com

Test report n°: 51.906

Page n° : 3 / 5

Petitioner: MOSAVIT

Date: 12/09/2012

DETERMINATION OF CRAZING RESISTANCE

*** GLAZED TILES ***

DESCRIPTION OF THE SAMPLE.-

Glass mosaic, 25 x 25 mm. Ref.:

-- **MOSAICO VITREO 25 x 25 mm** --

Code lab.: 299-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 11:1997**)

* Number of tiles tested: **Twenty-five**

* Number of tiles showing crazing: **Not - one.**

* Description of crazing: The tiles tested are free from crazes on the glazed surface.



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL INGENIEROS INDUSTRIALES
CASTELLÓN



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLÓN

C.I.F.: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLÓN
TEL: 964 208 583 - FAX: 964 723 141
www.laboratoriocarpi.com

Test report nº: 51.906

Page nº : 4 / 5

Petitioner: MOSAVIT

Date: 12/09/2012

DETERMINATION OF CHEMICAL RESISTANCE

DESCRIPTION OF THE SAMPLE.-

Glass mosaic, 25 x 25 mm. Ref.:

-- **MOSAICO VITREO 25 x 25 mm** --

Code lab.: 299-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 13:1998**)

* Number of test specimens used with each test solution: FIVE.

<u>Test solutions</u>	<u>Classification</u>	<u>Visual Changes</u>
* <u>Household chemicals</u> - Ammonium Chloride	GA	- No visible effects.
* <u>Swimming pool salts</u> - Sodium Hypochlorite	GA	- No visible effects.
* <u>Acids and Alkalis</u> (Low concentrations) - Hydrochloric Acid - Citric Acid - Potassium Hydroxide	GLA GLA GLA	- No visible effects. - No visible effects. - No visible effects.
* <u>Acids and Alkalis</u> (High concentrations) - Hydrochloric Acid - Lactic Acid - Potassium Hydroxide	GHA GHA GHA	- No visible effects. - No visible effects. - No visible effects.



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL INGENIEROS INDUSTRIALES
CASTELLÓN



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLÓN

C.I.F.: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLÓN
TEL: 964 208 583 - FAX: 964 723 141
www.laboratoriocarpi.com

Test report nº: 51.906

Page nº: 5 / 5

Petitioner: MOSAVIT

Date: 12/09/2012

DETERMINATION OF RESISTANCE TO STAINS

DESCRIPTION OF THE SAMPLE.-

Glass mosaic, 25 x 25 mm. Ref.:

-- **MOSAICO VITREO 25 x 25 mm** --

Code lab.: 299-12

RESULTS.- (Test performed after **UNE-EN-ISO 10545 Part 14:1998**)

* Number of test specimens used with each test solution: FIVE.

<u>Staining Agents</u>	<u>Cleaning Procedure</u>	<u>Class</u>	<u>Observations</u>
* <u>Stains having tracing action</u> (Pastes). - Green staining agent in light oil.....	- Running hot water for five minutes. (Procedure A).	5	- Stain removed.
* <u>Stains having chemical / oxidizing action</u> - Iodine alcohol solution	- Running hot water for five minutes. (Procedure A).	5	- Stain removed.
* <u>Stains having filming action</u> - Olive oil	- Running hot water for five minutes. (Procedure A).	5	- Stain removed.

* Observations: The chromium oxide used as green staining agent have a grain size less than 80 microns, being the 50 % (m/m) of theirs down on 3 microns.



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL INGENIEROS INDUSTRIALES
CASTELLÓN